



TECHNICAL DATA SHEET

P.E.E.K. (Poly Ether Ether Ketone) "PEEK"

Rod Sheet Colour: OFF-White

GENERAL

Density	1,3 g/cm ³	ISO 1183	DIN 53479
Water absorption in air 50% r.h.	0,1 %	ISO 62	DIN 53715
Absorption 23-C in water-saturation	0,5 %	ISO 62	DIN 53495
Food Compliance - YES		FDA / BfR	

MECHANICAL PROPERTIES

Tensile stress at yield at break	95 N/mm ²	ISO 527	DIN53455
Elongation at break	25 %	ISO 527	DIN53455
Tensile Modulus of elasticity	3000 N/mm ²	ISO 527	DIN53455
Compression test 1% strain 1000h	80 N/mm ²	ISO 899	DIN53444
Impact strength Charpy 7,5 J	no break	ISO R179	DIN53453
Notched impact strength Charpy	-	ISO179/3C	DIN53453
Ball indentation hardness	-	ISO2039.1	DIN53456
Rockwell hardness (dry)	M100	ISO2039.2	DIN53456
Coefficient of friction to steel ^[12]	0,38	ISO 8295	DIN 53375

THERMAL PROPERTIES

Melting point	340 °C	ISO 3146	
Thermal conductivity	0,25 W/(km)	ISO 22007.2	DIN 52612
Deformation at temperature HDT ^[15]	140 °C	ISO75	DIN 53461
Linear expansion coefficient 23-60°C	50 x 10 ⁻⁶ K ⁻¹	ISO 11359	DIN 53752
Operating temperature continuously ^[17]	260 °C		
Operating temperature short period-no load ^[18]	300 °C		
Minimum operating temperature ^[19]	-50 °C		
Flammability UL 94 (3-6 mm thickness)	V0		UL94
Oxygen index (LOI)	40 %	ISO4589	DIN 22117

ELECTRICAL PROPERTIES

Dielectric constant at 1 MHz.	3,2	ISO 250	DIN 53483
Dielectric strength	20 KV/mm	ISO 243	DIN 53481
Volume resistivity	10 ¹⁷ Ωcm	ISO 93	DIN 53482
Dissipation factor tan Δ at 1MHz	0,003	ISO 250	DIN 53483

Characteristics:

- Excellent Mechanical Properties
- Excellent Thermal Properties
- Superior Wear / Creep Resistance
- Excellent Dimensional Stability
- Excellent Radioactive Properties
- Non Flammability

Applications:

- Compressor Valves & Rings
- Transmission Components
- Centrifugal Pump Wear Parts
- Etch Rings
- Wafer Chucks
- Precision Cutting Blades
- Test Sockets

Please Note: The above Technical Data Sheet is a general guide to the physical properties of the material. This information is given without Warranty or Liability. It is the customers responsibility to determine if this product is suitable for the application.